



Speeding you to market

Aquaseal™

The **watertight**
decorative overlay

Technical Performance Data

AQUASEAL – 1.6 MILS WHITE – Stipple Finish

TESTS	Test Method	Typical Values	
Scratch Resistance (g)	CDM Test Method Hoffman Scratch	300	
Water Hold Out (hours)	NEMA	48 minimum	
Steam Test	NEMA	NO EFFECT	
Cleanability / Stain Resistance	NEMA LD 3.4 –2000	Stain	Clean
		<i>Distilled Water</i>	Stain
<i>Ethyl Alcohol Solution</i>	NE: No Effect	<i>NE=0</i>	<i>0</i>
<i>Acetone</i>	M: Moderate	<i>NE=0</i>	<i>0</i>
<i>Household Ammonia</i>	S: Severe	<i>NE=0</i>	<i>0</i>
<i>10% Citric Acid</i>		<i>NE=0</i>	<i>0</i>
<i>Vegetable Oil</i>	Clean	<i>NE=0</i>	<i>0</i>
<i>Fresh Coffee</i>	0: Easy	<i>NE=0</i>	<i>0</i>
<i>Fresh Tea</i>	4: Difficult	<i>NE=0</i>	<i>0</i>
<i>Catsup</i>	5: Permanent Stain	<i>NE=0</i>	<i>0</i>
<i>Yellow Mustard</i>		<i>S=2</i>	<i>5</i>
<i>10% Povidone Iodine</i>		<i>S=2</i>	<i>5</i>
<i>Black Permanent Marker</i>		<i>NE=0</i>	<i>0</i>
<i>#2 Pencil</i>		<i>NE=0</i>	<i>2</i>
<i>Wax Crayon</i>		<i>NE=0</i>	<i>2</i>
<i>Black Paste Shoe Polish</i>		<i>NE=0</i>	<i>2</i>
MEK Resistance (RUBS)	CDM Test Method	>200	

Approved: Michel Fortin, Eng., Technical Sales Manager

Revised: December 2008