



Speeding you to market



Technical Performance Data

Eclipse Paper Collection

Tests	Test Method	Typical Values	
Scratch Resistance (g)	Test Method Hoffman Scratch	25	
High Temperature Resistance	NEMA LD 3.6 –2000	NE	
Abrasion Resistance (cycles)	CDM Test Method Calibrase wheel CS-10 500g weight	15	
Cleanability / Stain Resistance	NEMA LD 3.4 –2000	Stain	Clean
<i>Distilled Water</i>	Stain	S	0
<i>Ethyl Alcohol Solution</i>	Ne: No Effect	M	0
<i>Acetone</i>	M: Moderate	NE	0
<i>Household Ammonia</i>	S: Severe	S	0
<i>10% Citric Acid</i>		M	0
<i>Vegetable Oil</i>	Clean	NE	0
<i>Fresh Coffee</i>	0: Easy	M	0
<i>Fresh Tea</i>	4: Difficult	M	0
<i>Catsup</i>	5: Permanent Stain	NE	2
<i>Yellow Mustard</i>		M	3
<i>10% Povidone Iodine</i>		M	0
<i>Black Permanent Marker</i>		S	5
<i>#2 Pencil</i>		NE	0
<i>Wax Crayon</i>		NE	1
<i>Black Paste Shoe Polish</i>		NE	0

Approved: Michel Fortin, Eng., Technical Sales Manager

Revised : December 2008