



Speeding you to market



Technical Performance Data

White Paper - Stipple finish

Tests	Test Method	Typical Values	
Scratch Resistance (g)	Test Method Hoffman Scratch	75-100	
High Temperature Resistance	NEMA LD 3.6 –2000	SL	
Abrasion Resistance (cycles)	CDM Test Method Calibrase wheel CS-10 500g weight	15	
Cleanability / Stain Resistance	NEMA LD 3.4 –2000	Stain	Clean
<i>Distilled Water</i>	Stain	S	5
<i>Ethyl Alcohol Solution</i>	NE: No Effect	S	5
<i>Acetone</i>	M: Moderate	M	5
<i>Household Ammonia</i>	S: Severe	S	5
<i>10% Citric Acid</i>		S	5
<i>Vegetable Oil</i>	Clean	S	5
<i>Fresh Coffee</i>	0: Easy	S	5
<i>Fresh Tea</i>	4: Difficult	S	5
<i>Catsup</i>	5: Permanent Stain	M	0
<i>Yellow Mustard</i>		S	5
<i>10% Povidone Iodine</i>		S	5
<i>Black Permanent Marker</i>		S	5
<i>#2 Pencil</i>		S	5
<i>Wax Crayon</i>		P	1
<i>Black Paste Shoe Polish</i>		S	5

Approved: Michel Fortin, Eng., Technical Sales Manager

Revised : December 2008