



Speeding you to market



## Technical Performance Data

### Solid Color Paper – Stipple finish

| TESTS                           | Test Method  | Typical Values         |          |
|---------------------------------|--|------------------------|----------|
| Scratch Resistance (g)          | Test Method<br>Hoffman Scratch                             | 100                    |          |
| High Temperature Resistance     | NEMA LD 3.6 –2000  | SL                     |          |
| Abrasion Resistance (cycles)    | CDM Test Method<br>Calibrase wheel<br>CS-10<br>500g weight | 15                     |          |
| Cleanability / Stain Resistance | NEMA LD 3.4 –2000  | Stain                  | Clean    |
|                                 |  | <i>Distilled Water</i> | Stain    |
| <i>Ethyl Alcohol Solution</i>   | NE: No Effect  | <b>S</b>               | <b>0</b> |
| <i>Acetone</i>                  | M: Moderate  | <b>NE</b>              | <b>0</b> |
| <i>Household Ammonia</i>        | S: Severe  | <b>S</b>               | <b>3</b> |
| <i>10% Citric Acid</i>          |  | <b>M</b>               | <b>0</b> |
| <i>Vegetable Oil</i>            | Clean  | <b>S</b>               | <b>5</b> |
| <i>Fresh Coffee</i>             | 0: Easy  | <b>M</b>               | <b>5</b> |
| <i>Fresh Tea</i>                | 4: Difficult   | <b>M</b>               | <b>2</b> |
| <i>Catsup</i>                   | 5: Permanent Stain   | <b>NE</b>              | <b>2</b> |
| <i>Yellow Mustard</i>           |  | <b>S</b>               | <b>5</b> |
| <i>10% Povidone Iodine</i>      |  | <b>M</b>               | <b>5</b> |
| <i>Black Permanent Marker</i>   |  | <b>M</b>               | <b>5</b> |
| <i>#2 Pencil</i>                |  | <b>NE</b>              | <b>2</b> |
| <i>Wax Crayon</i>               |  | <b>NE</b>              | <b>3</b> |
| <i>Black Paste Shoe Polish</i>  |  | <b>M</b>               | <b>5</b> |

Approved: Michel Fortin, Eng., Technical Sales Manager

Revised : December 2008