



Speeding you to market



## Technical Performance Data

### Light weight Print - Regular finish

Tests	Test Method	Typical Values	
Scratch Resistance (g)	Test Method Hoffman Scratch	25-50	
High Temperature Resistance	NEMA LD 3.6 –2000	NE	
Abrasion Resistance (cycles)	CDM Test Method Calibrase wheel CS-10 500g weight	15	
Cleanability / Stain Resistance	NEMA LD 3.4 –2000	Stain	Clean
<i>Distilled Water</i>	Stain	<b>S</b>	<b>0</b>
<i>Ethyl Alcohol Solution</i>	NE: No Effect	<b>M</b>	<b>0</b>
<i>Acetone</i>	M: Moderate	<b>NE</b>	<b>0</b>
<i>Household Ammonia</i>	S: Severe	<b>S</b>	<b>0</b>
<i>10% Citric Acid</i>		<b>M</b>	<b>0</b>
<i>Vegetable Oil</i>	Clean	<b>NE</b>	<b>0</b>
<i>Fresh Coffee</i>	0: Easy	<b>M</b>	<b>2</b>
<i>Fresh Tea</i>	4: Difficult	<b>M</b>	<b>0</b>
<i>Catsup</i>	5: Permanent Stain	<b>NE</b>	<b>2</b>
<i>Yellow Mustard</i>		<b>M</b>	<b>3</b>
<i>10% Povidone Iodine</i>		<b>M</b>	<b>0</b>
<i>Black Permanent Marker</i>		<b>S</b>	<b>5</b>
<i>#2 Pencil</i>		<b>NE</b>	<b>2</b>
<i>Wax Crayon</i>		<b>NE</b>	<b>3</b>
<i>Black Paste Shoe Polish</i>		<b>M</b>	<b>3</b>

Approved: Michel Fortin, Eng., Technical Sales Manager

Revised : December 2008