



Speeding you to market



## Technical Performance Data

### Light weight black - Regular finish

Tests	Test Method	Typical Values		
Scratch Resistance (g)	Test Method Hoffman Scratch	25		
High Temperature Resistance	NEMA LD 3.6 –2000	NE		
Abrasion Resistance (cycles)	CDM Test Method Calibrase wheel CS-10 500g weight	30		
Cleanability / Stain Resistance	NEMA LD 3.4 –2000	<b>Stain</b>	<b>Clean</b>	
		<i>Distilled Water</i>	Stain	<b>S</b>
	<i>Ethyl Alcohol Solution</i>	NE: No Effect	<b>M</b>	<b>0</b>
	<i>Acetone</i>	M: Moderate	<b>NE</b>	<b>0</b>
	<i>Household Ammonia</i>	S: Severe	<b>S</b>	<b>0</b>
	<i>10% Citric Acid</i>		<b>M</b>	<b>0</b>
	<i>Vegetable Oil</i>	Clean	<b>NE</b>	<b>5</b>
	<i>Fresh Coffee</i>	0: Easy	<b>M</b>	<b>0</b>
	<i>Fresh Tea</i>	4: Difficult	<b>M</b>	<b>0</b>
	<i>Catsup</i>	5: Permanent Stain	<b>NE</b>	<b>0</b>
	<i>Yellow Mustard</i>		<b>M</b>	<b>5</b>
	<i>10% Povidone Iodine</i>		<b>M</b>	<b>0</b>
	<i>Black Permanent Marker</i>		<b>S</b>	<b>0</b>
	<i>#2 Pencil</i>		<b>NE</b>	<b>1</b>
	<i>Wax Crayon</i>		<b>NE</b>	<b>1</b>
	<i>Black Paste Shoe Polish</i>		<b>M</b>	<b>5</b>

Approved: Michel Fortin, Eng., Technical Sales Manager

Revised : December 2008